

检验报告

TEST REPORT

报告编号: WT40103241155435WT1

第 1 页 共 6 页

委托单位 : 深圳市中履鞋业有限公司
委托单位地址 : 深圳市龙岗区布吉南湾街道坪埔路 13 号科柔大厦
样品名称 : 科柔 家居防滑拖鞋
型号/规格/等级 : -----
检验类别 : 送样检验
检验地址 : 龙华实验基地

深圳市计量质量检测研究院
(检验检测专用章)

批准人: 孟云

签发日期: 2024 年 11 月 27 日

签名:

孟云



扫码下载报告/辨真伪

报告首页背面“重要声明”是报告的组成部分,任何未包含“重要声明”内容的复制均为不完整复制。

深圳市计量质量检测研究院 Shenzhen Academy of Metrology & Quality Inspection <http://www.smq.com.cn>

电子邮件(E-mail): kfzx@smq.com.cn 客户服务热线(Customer Service Hotline): 400-900-8999

龙华实验基地: 深圳市龙华区民治大道民康路北 114 号 邮编: 518131

Longhua Experimental Base: No.114, Minkang North Road, Minzhi Avenue, Longhua District, Shenzhen

重要声明

Important statement

1. 本院是深圳市人民政府依法设置的产品质量监督检验机构，系社会公益型非营利性技术机构，为各级政府执法部门进行监督管理提供技术支持和接受社会各界的委托检验。

SMQ is a legal non-profit technical institute established by Shenzhen Municipal Government to undertake the quality supervision and inspection of products, and to provide technical support to relevant supervision and administration and also conduct commission test from the society.

2. 本院保证检验的科学性、公正性和准确性，对检验的数据负责，并对委托单位所提供的样品和技术资料保密。

SMQ is committed to assuring the scientificness, impartiality and accuracy of all tests carried out, responsibility for test data gained, and keeping confidential of all test samples and technical documents provided.

3. 抽样按照本院程序文件《抽样程序》和相应产品的检验细则的规定执行。

The sampling should be carried out according to the "sampling procedure" defined in the Procedure Document and relevant testing specifications.

4. 报告/证书无主检、审核、批准人签字，或涂改，或未盖本院报告/证书专用章及骑缝章无效。未经本院许可，不得部分复印、摘用或篡改本报告/证书内容。复印证书/报告未重新加盖本院证书/报告专用章无效。

Any report/certificate having not been signed by relevant responsible engineer, reviewer or authorized approver, or having been altered without authorization, or without both the Dedicated Report/Certificate Seal and its across-page seal is deemed to be invalid. Copying or excerpting portion of, or altering the content of the report/certificate is not permitted without the written authorization of SMQ. Any copy of certificates/reports without the Dedicated Report/Certificate Seal is deemed to be invalid.

5. 送样委托检验结果仅对来样有效：委托检验的样品、样品及委托方信息均由委托方提供，本院不对样品的代表性、真实性及信息的完整性和准确性负责。

The test results presented in the report apply only to the tested sample. The customer provides thier own information, the sample, and the sample information. Thus, SMQ assumes no responsibility for representativeness , authenticity of the sample and validity and accuracy of the information..

6. 未经检验机构同意，样品委托人不得擅自使用检验结果进行不当宣传。

Any use of SMQ test result for advertisement of the tested material or product must be approved in writing by SMQ.

7. 无 CMA 标志的报告/证书，仅作为科研、教学或内部质量控制之用。含粤字编号的 CAL 标志仅适用于产品标准和判定标准。

The non-CMA report/certificate issued by SMQ is only permitted to be used for research, teaching or internal quality control. CAL logo with symbol "Yue" is only relevant to product standards and reference of standards.

8. 委托方对报告/证书有异议的，应于报告发出之日起十五日内向本院提出。政府行政管理部门下达的监督检查任务，受检方对报告/证书有异议的，应按政府行政管理部门文件规定及国家相关法律、法规进行。

Any objection to report/certificate issued by SMQ should be submitted to SMQ within 15 days after the issuance of the test. The mandatory inspection assigned by government administrative departments shall be carried out in accordance with the documents and regulations of the government administrative department and relevant national laws and regulations if inspected parties raise any objection to the inspection.

9. 报告/证书更改后，发出的电子版报告/证书、报告/证书的扫描件及传真件将不被追回，委托方有义务将更改后的报告/证书提供给使用原报告/证书的相关方。

SMQ is not responsible for recalling the electronic version of the original report/certificate when any revision is made to them. The applicant assumes the responsibility of providing the revised version to any interested party who uses them.

10. 只申领电子报告时，相关内容和效力以电子报告为准；电子报告和纸质报告同时申领时，电子报告仅作为纸质报告的副本，相关内容和效力以同编号纸质报告为准。

The relevant content and effectiveness is subject to the electronic version of the original report which was only applied for. When an electronic report and a paper report are applied for at the same time, the electronic report is only a copy of the paper report, and the relevant content and effectiveness is subject to the paper report.

11. 检验报告二维码具浏览和下载完整报告功能，是应委托方要求所设，该二维码及其复制图能使任何人扫描获取完整的检验报告电子版，本报告持有人如需限制他人经该二维码获取检验报告内容，应自行遮盖或消除检验报告及其复制件所附二维码，我院对委托方选择检验报告二维码功能所致的信息泄露概不负责（适用于附二维码报告）。

The QR code has the function of browsing and downloading complete report. Setting this function or not is chosen by the customer. The QR code and its copy enable anyone to scan and obtain the complete electronic version of the test report. Thus, if the owner of this report needs to restrict others from obtaining the content of the test report through the QR code, he shall cover or remove the QR code attached to the test report and its copies by himself. SMQ assumes no responsibility for the information leakage caused by the customer's selection of the QR code function of the test report (This clause applies to reports with QR code attached) .

投诉及报告/证书真伪查询电话

Complaint hotline : 400-900-8999 按 5

Email : complaint@smq.com.cn

检验报告

报告编号: WT40103241155435WT1

第 2 页 共 6 页

样品信息:

样品名称: 科柔 家居防滑拖鞋
商标: 科柔 KENROLL
型号/规格/等级: -----
样品编/批号: KW286/KM286/KK288/KW214/KM311/KW277/KM276/KM268/KK343/K278/K267/K272
/KW228/KK223/KK215/KK211/KM201/KW203/KM211/KM9/KPW9/KPK9/KW6/KW176/
KM177/KW5/F201/F004/F102/R4W/KK9S/KW287/KK282
生产日期: ----- 抽样日期: -----
生产单位: -----
生产单位地址: -----
样品数量: 3 双 抽样基数: -----
抽样地点: -----
抽样人员: -----
检前样品描述: 正常

客户信息:

委托单位: 深圳市中履鞋业有限公司
委托单位地址: 深圳市龙岗区布吉南湾街道坪埔路 13 号科柔大厦
委托单位电话: 13502813237
邮政编码: -----
受检单位: -----

检验信息:

委托日期: 2024 年 11 月 23 日 委托单号: 8834901
检验类别: 送样检验 获样方式: 送样
检验日期: 2024 年 11 月 23 日~2024 年 11 月 27 日
检验环境条件: 温度: (18~25) °C, 湿度: (45~70) %RH
判定依据: Q/ZL 003-2024 (公开 2024 年 04 月 27 日 10 点 10 分)
检测依据: 见附页

检验结论:

检验结果见附页。

主检: 雷波

雷波

审核: 杨兴

杨兴

检验报告

报告编号: WT40103241155435WT1

第 3 页 共 6 页

检验项目	判定依据	结论
游离或可部分水解的甲醛含量	Q/ZL 003-2024 (公开 2024 年 04 月 27 日 10 点 10 分)	不适用
可分解致癌芳香胺染料	Q/ZL 003-2024 (公开 2024 年 04 月 27 日 10 点 10 分)	不适用
异味	Q/ZL 003-2024 (公开 2024 年 04 月 27 日 10 点 10 分)	符合
感官质量	Q/ZL 003-2024 (公开 2024 年 04 月 27 日 10 点 10 分)	符合
剥离强度	Q/ZL 003-2024 (公开 2024 年 04 月 27 日 10 点 10 分)	不适用
拉伸强度	Q/ZL 003-2024 (公开 2024 年 04 月 27 日 10 点 10 分)	符合
外底耐磨性能	Q/ZL 003-2024 (公开 2024 年 04 月 27 日 10 点 10 分)	符合
粘合强度	Q/ZL 003-2024 (公开 2024 年 04 月 27 日 10 点 10 分)	符合
外底防滑性能 (湿态动摩擦系数) [湿态动摩擦系数]	Q/ZL 003-2024 (公开 2024 年 04 月 27 日 10 点 10 分)	符合
标志	Q/ZL 003-2024 (公开 2024 年 04 月 27 日 10 点 10 分)	符合
帮带拔出力	Q/ZL 003-2024 (公开 2024 年 04 月 27 日 10 点 10 分)	不适用
衬里和内垫摩擦色牢度	Q/ZL 003-2024 (公开 2024 年 04 月 27 日 10 点 10 分)	不适用
外底防滑性能 (湿态动摩擦系数) [干态动摩擦系数]	Q/ZL 003-2024 (公开 2024 年 04 月 27 日 10 点 10 分)	符合

检 验 报 告

报告编号: WT40103241155435WT1

第 4 页 共 6 页



检 验 报 告

报告编号: WT40103241155435WT1

第 5 页 共 6 页

检验项目	方法标准	标准要求	实测结果	检验结论
外底防滑性能 [干态动摩擦系数]	GB/T 3903.6-2017	干态动摩擦系数 ≥ 0.55	0.82	符合
外底防滑性能 [湿态动摩擦系数]	GB/T 3903.6-2017	湿态动摩擦系数 ≥ 0.45	0.76	符合
粘合强度 (N/cm)	GB/T 532-2008	≥ 12	15.0 试验中, 分离均发生在被粘合材料内部	符合
标志 1. 鞋 2. 包装 (含吊牌) 3. 标识的形式和要求	Q/ZL 003—2024	每只鞋上至少应标注商标、鞋号, 企业还可以根据需要标注: 货号等。 至少应标注: 商标、产品名称、鞋号、材质、产地、企业名称及联系方式、执行标准编号、货号、合格(检验)标识。企业还可以根据需要标注: 三包规定、生产日期、颜色等。 应符合 QB/T2673-2023 的要求。	符合 符合 符合	符合
外底耐磨性能(磨痕长度/mm)	GB/T 3903.2-2017	≤ 15.0	1#左: 10.3 1#右: 10.4	符合
拉伸强度(MPa)	GB/T 1040.2-2022	≥ 1.2	裁刀类型:1A 1#:1.65 2#:1.66 3#:1.65 4#:1.64 5#:1.67	符合
衬里和内垫摩擦色牢度(沾色/级)	QB/T 2882-2007	其他材质: ≥ 3 绒面革: ≥ 2	---- (注: 橡塑材料)	不适用
帮带拔出力(N)	GB/T 38011-2019	冷粘、缝制、粘缝工艺的拖鞋 ≥ 80 铆钉等组装工艺的拖鞋 ≥ 50 材料撕裂而帮底粘合部位帮带未拉出时, 帮带拉出强度 ≥ 30 N/cm	---- (注: 一体成型拖鞋)	不适用

检验报告

报告编号: WT40103241155435WT1

第 6 页 共 6 页

检验项目	方法标准	标准要求	实测结果	检验结论
帮底剥离强度 (N/cm)	GB/T 3903.3- 2011	≥ 25	---- (注:露趾拖鞋)	不适用
感官质量	GB/T 3903.5- 2011	整鞋端正、平服、清洁。鞋内不露 钉尖,无钉尾突出。内垫贴服。子 口整齐严实。	符合	符合
异味(级)	QB/T 4552- 2020	≤ 3	2	符合
可分解芳香胺 染料(mg/kg)	GB/T 17592- 2011 GB/T 19942- 2019	纺织物 ≤ 20 皮革和毛皮 ≤ 30	---- (注:无纺织品、皮革和毛皮 部位。)	不适用
游离或可部分 水解的甲醛含 量(mg/kg)	GB/T 19941.1- 2019 GB/T 2912.1- 2009	直接与脚接触的材料 ≤ 75 不直接与脚接触的材料 ≤ 300	---- (注:无纺织品、皮革和毛皮 部位)	不适用

注:

- 1.本报告标志检测结果不包括内容真实性的核实。
- 2.我院获 CNAS 认可能力范围未涉及 Q/ZL 003-2024 (公开 2024 年 04 月 27 日 10 点 10 分)。

以下空白